Technical Data Sheet



30327 07.04.20

ULANO QXO

Solvent resistant, one-component photopolymer emulsion

ULANO QXO is used for the production of high-quality, solvent resistant stencils. Good resolution and excellent mesh bridging make it suitable for the use in Computer-to-Screen (CtS) units. **ULANO QXO** is resistant against plastisol inks. Use solvent-based cleaning systems for screen cleaning.

SENSITIZING

Not applicable as ready-to-use. However, to achieve very high printing resistance, e.g. when using aqueous or very aggressive discharge inks, ULANO QLO can additionally be sensitized with DIAZO C62 or DIAZO C10-D (depending on the emulsion package size). The sensitized emulsion can be stored at least 2 weeks (at 20-25°C). The small Diazo bottle is filled to the mark, the large bottle to the bottle shoulder with distilled water. Close the bottle and shake well. After a maximum of 15 minutes give the diazo solution to the emulsion and stir until the mixture has homogenized. Allow the sensitized emulsion to degas for at least one hour before use.

DEGREASING

Before coating it is recommended to clean and degrease the screen mesh to achieve reproducible coating results. Ensure proper tension of the screen mesh. Use one of our manual degreasers or degreasing concentrates for automatic units. After thorough rinsing with water and drying, the screens are ready for coating.

COATING

Coating can be done manually or by machine.

DRYING

The screen must be dried thoroughly before exposing to achieve the highest ink resistance. This should preferably be done in a dust-free drying-chamber with fresh-air inlet at temperatures of between 35-40°C. In case of large sized screens which do not fit into the drying chamber, at least increase the room temperature (e.g. with an electric heater) and ventilate the humidity

EXPOSURE

The stencil is created by UV-light hardening of the non-printing stencil parts. Expose with blue actinic light at a wave length of 320-420 nm. Most suitable exposure sources are metal halide lamps or digital exposure units (CTS). Due to the variation of exposure units, trials for the determination of the correct exposure time are essential. Please contact the machine manufacturer or as ULANO for advise.

RETOUCHING / BLOCKING-OUT

For retouching / blocking-out use products of our screenfiller range. When printing with aqueous inks, preferably use water based products. These dry water resistant and can be removed with decoating products and a high pressure water washer. Ask your distributor or ULANO for advice.

This data sheet is for your information. A legally binding assurance of the product's suitability for a specific purpose cannot be derived from it and no liability can be assumed for any potential damages that may occur. Liability for damages due to a slightly negligent breach of duty on our part or on the part of our legal representative or vicarious agent is excluded. Our liability for damages due to injury to life, body or health is not covered by this limitation of liability. Our products are subject to continuous production and quality control and leave our company in perfect condition.

This product is intended solely for industrial applications and not for use by the end consumer. We recommend to our customers to always test the product themselves since only in this way – also after production – can the freedom from certain substances and the suitability for a particular purpose be verified. The user has to test the product for suitability for the intended application. We reserve the right to modify product specifications. Tests that are not part of the specifications of the product mentioned above have not been carried out. All information applies only to the above-mentioned product obtained from Kissel + Wolf GmbH. It corresponds to our current state of knowledge, but is not a confirmation of a particular application and is not automatically replenished. All information is valid for a maximum of 12 months from the date stated above (annexes may be provided with their own date). Any industrial property rights as well as existing laws and regulations are to be observed by the recipient of our product on his own responsibility. Intellectual property rights of third parties must be observed. Our terms and conditions of sale and delivery shall apply.

Technical Data Sheet



Page 2 of 2

DECOATING

In general, stencils made using **ULANO QXO** can easily be decoated. Use one of our post-cleaners to remove possibly remaining ink residue or so-called ghost images which may remain on the screen after decoating. Trials are essential as the type of residue may vary. Please ask for samples to test.

NOTICE

Please note that the printing resistance of a screen-printing stencil is influenced by a lot of parameters e.g. mesh, coating technique, drying, exposure time etc. Furthermore, a lot of printing media and printing machines are being used in practice which have not all been tested by us. Therefore, please accept our offer and test the suitability of our products by asking for emulsion samples, as we can only guarantee for a constant quality according to our own working conditions.

COLOUR Orange

VISCOSITY Approx. 5300 mPas (Rheomat RM 180, MS 33, D = 100 s^{-1} , 23°C)

HEALTH HAZARDS / ENVIRONMENTAL PROTECTION

Please follow information given in the safety data sheet.

STORAGE 1 year (at 20-25°C). Protect against freezing.

Screens coated in advance: at least 4 weeks (at 20°C and in complete darkness).

Dry again prior to copying.